

JP 08-099,080
[claims only, as requested]

Translated from Japanese by the Ralph McElroy Co., Custom Division
P.O. Box 4828, Austin, Texas 78765 USA

Code: 282-62286

JAPANESE PATENT OFFICE

PATENT JOURNAL

KOKAI PATENT APPLICATION NO. HEI 8[1996]-99080

Technical Disclosure Section

Int. Cl. ⁶ :	C 02 F 1/28 B 01 D 15/00 C 02 F 1/50 C 02 F 1/50
Application No.:	Hei 6[1994]-236363
Application Date:	September 30, 1994
Publication Date:	April 16, 1996
No. of Claims:	3 (Total of 6 pages: OL)
Examination Request:	Not requested

FILLING MATERIAL FOR FILTRATION

Inventors:	Shinya Matsumoto 1023-1, Yamazaki, Oaza, Shimamoto-cho, Mishima-gun, Osaka-fu (Bioprocess Development Center of Santory)
------------	---

F:

Shinichi Kunizaki
1023-1, Yamazaki, Oaza,
Shimamoto-cho,
Mishima-gun, Osaka-fu
(Bacteria Center of
Technical Development
Center of Santory)

Mitsunobu Masuda
1-3-23, Dojimahama,
Kita-ku, Osaka-shi,
Osaka-fu (Takuma)

Jun Kawaguchi
1-3-23, Dojimahama,
Kita-ku, Osaka-shi,
Osaka-fu (Takuma)

Ken Morimoto
1-3-23, Dojimahama,
Kita-ku, Osaka-shi,
Osaka-fu (Takuma)

Applicants:

000001904
Santory Ltd.
2-1-40, Dojimahama,
Kita-ku, Osaka-shi,
Osaka-fu

000133032
K.K. Takuma
1-3-23, Dojimahama,
Kita-ku, Osaka-shi,
Osaka-fu

Agent:-

Osamu Kitamura,
patent attorney

* * *

Claims

1. A filling material for filtration containing activated carbon layer (1) on which a highly dense nonwoven fabric layer (2) is laminated in the direction of water flow.

2. The filling material for filtration described in Claim 1, containing both the above-mentioned activated carbon layer (1) and a highly dense nonwoven fabric layer (2) homogeneously dispersed with an antibacterial material made with a synthetic insoluble inorganic material either to which silver ions are bonded or on which a silver compound is deposited, in an amount necessary to obtain a silver content of 0.05-1.0% for both the activated carbon layer (1) and the highly dense nonwoven fabric layer (2).

3. The filling material for filtration described in Claim 1, containing both an activated carbon layer (1) homogeneously dispersed with an antibacterial material made with a synthetic insoluble inorganic material either to which silver ions are bonded or on which a silver compound is deposited, in an amount necessary to obtain a silver content of 0.05-1.0% for the above-mentioned activated carbon layer (1) and highly dense nonwoven fabric layer (2) consisting of the fibers containing an antibacterial material made with a synthetic insoluble inorganic material either to which silver ions are bonded or on which silver compound is deposited, in an amount necessary to obtain a silver content of 0.05-1.0% for the fibers of the highly dense nonwoven fabric layer (2).

* * *